













Technical Data Sheet

KF Series
Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Antique		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Hartford Red		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Heritage Red S		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Heritage S		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Heritage SWB		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Mohawk		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Old Mystic		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Princess Royal		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Red Matt		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
Rocky Mountain		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
University Blend Dark		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25
University Blend Red		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<34	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.5	530	6.86