



TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on Brick conducted in accordance with ASTM C67-14 Standard Method for Sampling and Testing

Brick and Structural Clay Tile

09/05/2016

Name:	Glen-Gery Corporation 433 S. Pottsville Pike Shoemakersville, PA 19555	Plant:	Hanley	*Temperature: 60 - 90F
Phone:	610-562-3076	Report Number:	GGHA-1467	*Humidity: 30% - 70%
Fax:	610-562-2084	Received Date:	07/27/2016	
		Sampled Date:	06/15/2016	
		Lot:	066RMDA	
		Product Code:	71203100	

Sample Description: **Hanley Clay/Shale Extruded**

						Average	Test Date
Absorption	1	2	3	4	5		
24 Hour Submersion in Cold Water (%)	2.99	2.93	2.70	2.55	2.96	2.83	08/10/2016
5 Hour Submersion in Boiling Water (%)	3.23	3.02	3.01	2.84	3.59	3.14	
Saturation Coefficient (Ratio of 24H to 5H)	0.93	0.97	0.90	0.90	0.83	0.90	
Compressive Strength	1	2	3	4	5	Average	
<i>psi</i>	13,653	18,694	16,965	12,910	17,182	15,881	08/05/2016
<i>MPa</i>	94.1	128.9	117.0	89.0	118.5	109.5	
Efflorescence	11	12	13	14	15		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		08/17/2016
IRA (Oven Dried Method)	6	7	8	9	10	Average	
<i>g/min/30 in.²</i>	2.5	3.4	3.3	3.0	2.9	3.0	08/12/2016

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 216 - 15 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW, with absorption alternate in section 7.1.2

ASTM C 32 - 13 Standard Specification for Sewer and Manhole Brick (Made From Clay or Shale)
Grade: SM, SS / MM, MS, with absorption alternate in Section 5.1

ASTM C 62 - 13a Standard Specification for Building Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW, NW, with absorption alternate in section 5.1.2

CAN/CSA-A82-06 Fired masonry brick made from clay or shale
Grade: EG

Michael Walker, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
The results shown above apply only to the samples tested, which are provided by the customer.
This test report shall not be reproduced except in full, without written approval of the laboratory.*